



TRI-BUILT® ASTM 226 TYPE II 30

USES & DESCRIPTION

TRI-BUILT® ASTM 226 TYPE II 30 is an asphalt saturated organic felt designed for use as an underlayment with asphalt shingles in commercial and residential applications.

Meets Florida Approval BFL #15067



SPECIFICATIONS

ASTM	D226 TYPE II
PLIABILITY, tested with 1/2" (13 mm) radius @ 77°F (25°C)	NO FAILURES
MOISTURE, at time of manufacturing	4.1%, max
LOSS ON HEATING, @221°F (105°C) for 5 hours	4%, max
NET MASS OF SATURATED FELT (lbs/100 ft ²)	26.0, min
MASS OF SATURANT (lbs/100 ft ²)	15.0, min
MASS OF DESATURATED FELT (lbs/100 ft ²)	10.0, min
ASH (desaturated felt mass)	10%, max
SATURATION	150% min