



TRIBUILT® NO. 15

USES & DESCRIPTION

TRIBUILT® #15 is an asphalt saturated organic felt designed for use as an underlayment with asphalt shingles in commercial and residential applications.



TYPICAL PROPERTIES (NON RATED #15 FELT)

PLIABILITY, tested with 1/2" (13 mm) radius @ 77°F (25°C)	NO FAILURES
MOISTURE, at time of manufacturing	4.3%, max
LOSS ON HEATING, @221°F (105°C) for 5 hours	4%, max
NET MASS OF SATURATED FELT (lbs/100 ft ²)	12.3, min
MASS OF SATURANT (lbs/100 ft ²)	6.2, min
MASS OF DESATURATED FELT (lbs/100 ft ²)	5.2, min
ASH (desaturated felt mass)	10%, max
SATURATION	120% min